

Ø filo mm	Ø filo JDP	matassa kg	L m ca.	L/kg m	bobina kg	spessore rivest. zinco µm	tolleranze* Ø fili ± mm
2,70	16	25/50	550/1100	22	500	~13	0,045
3,50	18	40/50	520/650	13	600/500	~15,5	0,060